





# DUPLEX R QUALITY

## DESCRIPTION & STRUCTURE ANALYSIS

Fully Coated WLC  
with grey back

	Multiple Pigment Coating
	Unprinted PIW
	Mechanical Pulp PCW + PIW
	PIW

## TECHNICAL SPECIFICATIONS

Basis Weight	Thickness	Stiffness Taber 15°	
		MD (gramf x cm) (c)	CD (gramf x cm) (c)
g/m <sup>2</sup> (a)	µm (b)		
300	360	120	42
350	425	190	70
400	485	260	100
450	555	350	140
500	620	440	175
550	700	510	205

<b>Humidity (%)</b>	6-8
<b>Brightness ISO (Elrepho) (%)</b>	Top 80 ± 2
<b>Cobb Test 1'</b>	Top Side 35-65
<b>Bulk</b>	1.23 cm <sup>3</sup> /g (d)
<b>Delamination (ft*lb*10<sup>-3</sup>)</b>	MD >= 50 CD >= 50
<b>Gloss</b>	40-55

*Tolerances	
	a (±3%)
	b (-5%)
	c (-15%)
	d (±5%)

### Storage conditions

The product should be kept in a clean, shadowy place, free of odors and dust with relative humidity 50% (±3%)

### The product is suitable for dry foodstuff packaging

The company reserves the right to change the technical specifications of its products