

# MM LINER

MML / LIN

Code no. 44103




Mill

Kolicevo Karton d.o.o. Proizvodnja kartona d.o.o., Slovenia

Last update of values 02.06.2020

## 1 Board structure



	% of total board	+/- in % of total
<b>PIW</b>	30	10
<b>PCW</b>	55	10
<b>Pigment coating</b>	15	5
<b>Total</b>	100	

## 2 Technical specifications

Grammage	Caliper	Burst strength	SCT cd
g/m <sup>2</sup>	µm	kPa	kN/m
180	200	360	2.6
195	225	380	2.8
210	245	400	2.9
230	270	420	3.1
250	310	440	3.3
280	350	470	3.6

Property	Value	Tolerances	Test standard
<b>Brightness top (% Elrepho)</b>	80	- 1	ISO 2470-2
<b>Smoothness PPS top (µm)</b>	2.0	≤ 2.5	ISO 8791-4
<b>Gloss 75° (%)</b>	> 45		ISO 8254
<b>Grammage (g/m<sup>2</sup>)</b>		+/- 2%	EN ISO 536
<b>Caliper (µm)</b>		+/- 5%	EN 20534
<b>Burst strength (kPa)</b>		- 10%	ISO 2759
<b>SCT cd (kN/m)</b>		- 0.3	ISO 9895
<b>Testing climate</b>	23°C	+/- 1°C	EN ISO 186
	50%	+/- 2% rh	
<b>Recyclability</b>	confirmed	in terms of the norm	EN 13430
<b>Biodegradability</b>	confirmed	in terms of the norm	EN 13432