

TECHNICAL SPECIFICATION

JANUARY 2020

SUBSTANCE	CALIPER	BULK	SCT CD	BURST	ROUGHNESS	COBB
ISO 536	ISO 534	ISO 534	ISO 9895	ISO 2759	ISO 8791-2	ISO 535
g/m ²	mm	cm ³ /g	KN/m	KPa	ml/min	g/m ²
(140)	0.148	1.06	2.3	270	50	70
(160)	0.170	1.06	2.7	280	50	70
180	0.194	1.08	2.9	320	50	70
195	0.210	1.08	3.0	340	50	70
210	0.232	1.10	3.3	360	50	70
230	0.255	1.11	3.6	385	50	70
250	0.280	1.12	3.9	410	50	70
270	0.306	1.13	4.3	425	50	/
290	0.347	1.20	4.5	450	50	/

() NON STANDARD GRAMMAGE, AVAILABLE ON SPECIAL REQUEST ONLY.

BRIGHTNESS (AT PRODUCTION)

TOP	83% +/- 2	ISO 2470-2
-----	-----------	------------

TOLERANCES - SAMPLING ISO 186

SUBSTANCE	+/- 3%	average of order
CALIPER	+/- 5%	for single determinations (95% of values)
SCT CD	- 10%	
BURST	- 20%	
ROUGHNESS	+ 20 ml/min	
COBB BACK	+/- 30 g/m ²	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

CERTIFICATIONS: ISO 9001 / ISO 14001 / ISO 50001 / OHSAS 18001
FSC® - C081817 CERTIFIED BOARD IS AVAILABLE ON REQUEST